

Data sheet

Spec.No.: S03200
Rev.: F

Quality characteristics

Textile test conditions in line with ASTM dtex acc. BISFA			YARN									CORD	
Linear density (nominal)	Number of filaments	Produced in	Linear density	Breaking force (cond.)	Elongation at 45N (cond.)	Elongation at break (cond.)	Breaking force (oven-dry)	Elongation at 45N (oven-dry)	Elongation at break (oven-dry)	Finish content	Wet shrinkage	Breaking force (oven-dry)	Twist (Z/S/m)
dtex	(nominal)		dtex	N	%	%	N	%	%	%	%	N	t/m
1220 S2	660	Czech Rep.	1240	55	9,4	11,5	64	5,1	9,2	0,4	8,5	120	550/550
1840 CS3	1000	Czech Rep.	1870	85	6,0	15,0	100	2,3	12,0	0,4	6,0	185	420/420
2440 CS3	1320	Czech Rep.	2440	115	3,3	16,0	135	1,5	12,9	0,4	6,0	235	385/385
1550 CS3	1000	Czech Rep.	1550	70	8,6	14,0	80	3,5	12,0	0,4	9,0	-	-
3680 CS3	2000	Czech Rep.	3740	170	1,4	16,0	200	0,6	12,3	0,4	9,0	338	320/320
4880 CS3	2640	Czech Rep.	4990	211	0,7	15,0	258	0,4	12,0	0,4	9,0	-	-

- Standard Product
- Special Product (on customer request)

date	prepared/approved/checked
department	29.03.16
name	Q
	M.Vymetalova,eh